



## CLIMAVER® Self-supporting Ducts

A rigid panel made of high density **ISOVER** glass wool covered on the outer surface with a decorative fibreglass fabric and an aluminium sheet which acts as a vapour barrier. On its inner surface, it is covered with a new glass-reinforced net fabric which is black in colour and has a high mechanical resistance.

Due to its excellent acoustic and good thermal performance, **CLIMAVER® A2 deco** is the ideal solution. It is capable of satisfying the most stringent requirements in terms of reaction to fire, for the installation of self-supporting duct systems to distribute air in exposed thermal installations without a false ceiling for the air-conditioning and ventilation of buildings.

### AESTHETICS.



Decorative aspect, rigid structure, vapour barrier and maximum protection in case of fire, without the need of additional exterior painting.

### AIR TIGHTNESS.



Class ATC1 according to new RITE regulation.

### SOUND INSULATION.



Optimal acoustic ambient quality and comfort class.

### EASY HANDLING.



Duct union continuity. Exclusive male/female leaning shiplaps of the panels.

### RECYCLED GLASS.



Sustainable product. Recycled material 55%. 100% recyclable.



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES				STANDARD
Thermal conductivity	T	[°C]	10	20	40	60	EN 12667 EN 12939
	$\lambda$	[W/(m·K)]	0.032	0.033	0.036	0.038	

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES						STANDARD		
Practical acoustic absorption coefficient, $\alpha_p$	-	Hz	$\alpha_w$	125	250	500	1000	2000	4000	-	EN ISO 354 EN ISO 11654
	$\alpha_p$	-	0,85 <sup>(1)</sup>	0.35	0.65	0.75	0.85	0.90	25		
Acoustic attenuation, in a straight duct, $\Delta L$ (DB/m)*	Section, S mm <sub>2</sub>	200 x 200	-	4.83	11.49	14.04	16.73	18.12	-		
		300 x 400		2.82	6.70	8.19	9.76	10.57			
		400 x 500		2.17	5.17	6.32	7.53	8.15			
		400 x 700		1.90	4.51	5.51	6.57	7.12			
		500 x 1000		1.45	3.45	4.21	5.02	5.44			

Acoustic trials with plenum: CTA 048/11/REV-5.

<sup>(1)</sup> Weighted acoustic absorption coefficient  $\alpha_w$ , without plenum 0.55 CTA 140053/REV-7.

\* Estimated by the formula:  $\Delta L = 1,05 \cdot \alpha_p \cdot 1,4 \cdot P/S$ , (P = perimeter) for the sound power of a ventilator with a 20,000 m<sup>3</sup>/h flow, load loss 15 mm ca.

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	STANDARD
Reaction to fire	-	Euroclass	A2-s1, d0	EN 13501-1 EN 15715
Resistance to the diffusion of water steam of mineral wool, $\mu$	MV	m	1	EN 12086
Resistance to the diffusion of water steam of facing	Z	m <sup>2</sup> ·h·P	> 140	EN 12086
Thickness of the air layer equivalent to water vapor diffusion, Sd	MU	m	100	EN 12086
Airtightness	-	Class	D Maximum class of watertightness (class ATC1) according to the new RITE regulation update.	UNE-EN 13403 EN 12237
Resistance to pressure	-	Pa	800	UNE-EN 13403
Dimensional stability, $\Delta\epsilon$	-	%	<1	EN 1604
Instructions for use	-	-	Consultar Manual de Montaje de conductos CLIMAVER. Información adicional disponible en: <a href="http://www.isover.es">www.isover.es</a>	-
Characteristics	-	-	Resistant to different cleaning methods. No proliferation of mould and bacteria. Available in a wide range of colours.	-
Working conditions	-	-	Air speed up to 18 m/s and circulating air temperature up to 90 °C.	-

**DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION\***

Thickness d (mm)	Length l (m)	Width b (m)	m <sup>2</sup> /pack	m <sup>2</sup> /pallet	m <sup>2</sup> /truck	Designation code
25	3.00	1.19	24.99	149.94	2399	MW-EN 14303-T5-MV1
25	3.00	1.19	24.99	149.94	2399	MW-EN 14303-T5-MV1
25	3.00	1.19	24.99	149.94	2399	MW-EN 14303-T5-MV1
25	3.00	1.19	24.99	149.94	2399	MW-EN 14303-T5-MV1
25	3.00	1.19	24.99	149.94	2399	MW-EN 14303-T5-MV1

\* Possibility to supply half pallets. Special colours available on request.



**CLIMAVER® A2 Deco**



**[www.isover.es](http://www.isover.es)**

*This data sheet was completed on the date indicated on the right-hand side and was done with ISOVER's knowledge and experience at that time. However, it does not offer any legal guarantee, unless it has been expressly agreed. Bearing in mind that our knowledge and developments of building solutions and products are continuously evolving, ensure that when you use this data sheet, it is the latest version. The description of the product applications does not take into account the special circumstances that may arise for a specific case. Please check that this product is the appropriate one for the application you are considering. For more detailed information, contact our network of ISOVER branches.*

**SAINT-GOBAIN ISOVER IBÉRICA, S.L. • C/ Príncipe de Vergara, 132 • 28002 Madrid • Spain**

APR-2024

